

Kaiflex adhesive 415plus Technical Data

Description	Special contact adhesive for use with all Kaiflex flexible insulation-systems. Perfect adhesion on metallic priming, no adhesion on asphalt, bitumen or lead oxide red coatings (linseed based oil).
Application range	Kaiflex adhesive 415plus is specially formulated for bonding Kaiflex flexible insulation systems, especially those with KaiCene-Technology (e.g. Kaiflex KKplus s1).
Base	Polychloroprene
Colour	yellow-red
Solid %	25 ±2 %
Temperature resistance	Up to +130 °C
Characteristics / Application	Stir up appropriately before use. Easy to spray, very good initial adhesion, good thermal resistance. Apply on both sides with brush or oder air brush. Flash-off time: 5 -20 minutes. After adherence press surfaces firmly together
Viscosity	8000 mPas (dyn.)
Density	0.90 g/cm³
Cleaning	Kaiflex Cleaner
Storage	Store dry, cool and frost-free (+15 to +23 °C) in tightly sealed original can
Shelf Life	Shelf life is up to 12 months in an unopened container when stored as directed. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. Please, follow the petroleum regulation and law of the land.
Application	Before use adhesive should be thoroughly stirred. Surfaces to be adhered together must be clean, dry and free of any dust or grease. Use a brush with short stiff bristles (e.g. Kaiflex brush can). Apply a thin even layer of adhesive to both surfaces. Allow the adhesive to become dry to touch. This will take 2 to 8 minutes, depending on ambient conditions. The drying time of adhesive will be adversely affected with high humidity (greater than 85 %) and low temperature (less than +5° C). Check the adhesive surface using the finger test. If the finger does not stick to the surface and the surface does not feel tacky, the joints should be closed. Press both surfaces to be bonded together under firm pressure. Joints made with Kaiflex adhesive 415plus shall be allowed a curing time of 36 hours at room temperature. Never allow to cure in bright sunlight. Never use the adhesive whilst installation is in operation. Leave adhesive joints for 36 hours before applying any coatings, jackets or adhesive tape.
Attention	Adequate ventilation must be maintained, particularly in confined spaces. Due to the volatile nature of the solvent, keep away from any source of ignition such as pilot lights or sparks. Prohibition of smoking must be rigidly enforced in the vicinity of use.
Health & Safety	<p>As with all chemicals, caution should always be exercised. Protective clothing such as gloves and goggles should be worn. Inhalation: Inhalation of vapour or mist should be avoided. If inhaled symptoms include coughing, wheezing, laryngitis, and shortness of breath, headache, nausea, and vomiting. Immediately shift victim to fresh air and if needed immediately start artificial respiration. Give oxygen if breathing is laboured. Get emergency medical help.</p> <p>After inhalation If inhaled, immediately take the affected person to fresh air. Give sufficient oxygen. If not breathing give artificial respiration. Get medical attention if symptoms develop.</p> <p>After skin contact Rinse with running water and soap. Remove all contaminated clothing.</p> <p>After eye contact In case of contact with the eyes rinse immediately with plenty of water and seek immediate medical attention.</p> <p>After ingestion Do not induce vomiting, seek medical advice immediately.</p> <p>Precaution Please refer to the appropriate material data sheet (MSDS) prior to using this product.</p>

Kaimann GmbH provides this information as a technical service. Where information is provided that is a direct result of Kaimann's own technical analysis and testing, the information displayed is an interpretation of the data accurate to the extent of our knowledge and ability as of date of printing. Standardised methods and procedures are used wherever possible. Some information presented may be derived from sources other than Kaimann and in these cases Kaimann is substantially, if not wholly, relying upon the other source(s) to provide accurate information.

Actual technical performance may be dependent on the specific installation and site conditions. Since Kaimann cannot control installation or site conditions, Kaimann does not guarantee that the user will obtain the same results as published in this document. It is the responsibility of each user to perform their own tests in order to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and/or any third party to which the user may convey the products.