

U SeaProtect Wired Mat

Wired Mats unfaced - density from 36 to 86 kg/m³

ULTIMATE mineral wool provides a unique high-performance profile: it combines safety, comfort and ease of handling.



Effective fire protection

ULTIMATE provides effective fire resistance, but also very good performance in reaction to fire



Excellent thermal insulation

Excellent thermal insulation combined with unique efficiency



Optimal acoustic performance

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties



Light weight

Increase insulation - reduce weight ULTIMATE combines high fire & thermal performance with very low weight











U SeaProtect Wired Mat



Wired Mats unfaced - density from 36 to 86 kg/m³

| Characteristic | Symbol | Unit | Quantities and measured values | | | | | Standard | | |
|--|-----------------|------------------|--|-------|-------|-------|-------|---------------------------------------|--|----------|
| Application fields | - | - | Thermal insulation. acoustic insulation and fire protection constructions in shipbuilding | | | | | - | | |
| Material | - | - | Mineral wool with quality mark RAL by the Gütegemeinschaft Mineralwolle e.V unrisky regarding health according to German decree on dangerous substances. decree on prohibition of chemicals and to Regulation (EC) N°1272/2008 | | | | | - | | |
| Thermal conductivity | Т | [°C] | 10 | 50 | 100 | 150 | 200 | 300 | 400 | |
| U SP WM 36 | $\lambda_{N.P}$ | [W/(m·K)] | 0.032 | 0.037 | 0.045 | 0.055 | 0.069 | 0.104 | 0.153 | EN 12667 |
| U SP WM 48 | $\lambda_{N.P}$ | [W/(m·K)] | 0.032 | 0.036 | 0.044 | 0.053 | 0.063 | 0.087 | 0.122 | |
| U SP WM 66 | $\lambda_{N.P}$ | $[W/(m\cdot K)]$ | 0.031 | 0.035 | 0.040 | 0.047 | 0.054 | 0.072 | 0.096 | |
| U SP WM 76 | $\lambda_{N.P}$ | $[W/(m\cdot K)]$ | 0.031 | 0.035 | 0.040 | 0.047 | 0.054 | 0.072 | 0.096 | |
| U SP WM 86 | $\lambda_{N.P}$ | $[W/(m\cdot K)]$ | 0.031 | 0.037 | 0.043 | 0.050 | 0.054 | 0.072 | 0.093 | |
| Thermal behaviour | - | - | Exposure to temperature until 650 °C (depends on density) is possible From 150 °C on the binder starts to volatilise | | | | | AGI Q 132 | | |
| Behaviour in fire | - | [°C] | Melting point according to DIN 4102, part 17: ≥ 1000 °C Non combustible according to IMO-Resolution Homologated for shipbuilding according to EC Type Examination Certificates Nr.: MED-B+D Certificate = visit our website | | | | | | DIN 4102-17 IMO-Resolution MSC.307(88)- (FTP-Code 2010) | |
| Specific thermal capacity | С | [kJ/(kg•K)] | ~ 1.03 | | | | | ISO 10456 | | |
| Water vapour diffusion resistance factor | μ | - | ~ 1.0 | | | | | ISO 10456 | | |
| Sound absorption value | α_{W} | - | U SeaProtect Wired Mat 48 100 mm: 1,00 U SeaProtect Wired Mat 66 40/50 mm: 1,00 | | | | | EN 11654 | | |
| Chemical behaviour | - | - | Sulphide free | | | | | - | | |
| Miscellaneous | - | - | ISOVER is certified according to DIN EN ISO 9001 and DIN EN ISO 14001 | | | | | ISO 9001 ISO 14001 EN ISO 50001 | | |

| Delivery form: Standard dimensions / packaging information* | | | | | | | |
|---|--------------|------------------------------------|--|--|--|--|--|
| | Width w (mm) | Thickness d (mm) | | | | | |
| U SeaProtect Wired Mat 36 | 600 mm | 50, 60, 70, 80, 100, 120 mm | | | | | |
| U SeaProtect Wired Mat 48 | 600 mm | 50, 80, 100 mm | | | | | |
| U SeaProtect Wired Mat 66 | 600 mm | 30, 40, 50, 60, 70, 80, 90, 100 mm | | | | | |
| U SeaProtect Wired Mat 76 | 600 mm | 30 mm | | | | | |
| U SeaProtect Wired Mat 86 | 600 mm | On request | | | | | |

^{*} Dimensions on request, products with minimum order quantities are requested

www.isover-technical-insulation.com

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.

